arXiv:1009.4770v1 [cond-mat.dis-nn] 24 Sep 2010

Artificial magnetism in theory of wave multiple scattering by random discrete non-magnetic conducting media

Yu.N.Barabanenkov[1], M.Yu.Barabanenkov[2], S.A.Nikitov[1]

[1] *V.A Kotelnikov Institute of Radioengineering and Electronics, Russian Academy of Sciences*
Mohovaya 11, 103907 Moscow, GSP–3, Russia
[2] *Institute of Microelectronics Technology, Russian Academy of Sciences*
142432 Chernogolovka, Moscow Region, Russia

We show that technique of Dyson equation in wave multiple scattering by spatially disordered discrete medium statistical theory leads directly to a dielectric permittivity tensor, which is characterized by spatial dispersion and obeys the generalized Lorentz–Lorenz formula. Introduced via this spatial dispersion an effective magnetic permeability demonstrates the diamagnetic property in limit of independent strongly reflected non–magnetic small spherical particles in accordance with earlier intuitive predictions. The revealed physical nature of the effective diamagnetic property consists in that electric and magnetic dipoles induced in a particle by wave scattering give different contribution into the transverse and longitudinal components of the effective dielectric permittivity. Besides as appeared the diamagnetism under study is enhanced by appearance of additional effective dielectric displacement current in the medium.

1 Introduction

Effective medium theory or homogenization approach is a powerful way to handle the radiative properties of composite materials, such as, e.g., cosmic dust, aerosols, porous media, and microstructured materials or "metamaterials". Several interesting potentials of these metamaterials have been demonstrated and/or suggested, including the realization of media with negative index of refraction [1, 2] and artificial magnetism from conductors [3, 4, 5]. Even though some fundamental concepts about the metamaterials such as negative permittivity and negative permeability are widely accepted and relatively well understood today, the problem to define unambiguously these parameters by systematic and clear way is not yet totally resolved. For example, the introducing artificial magnetism by [3, 4, 5] is rather intuitive one. The two variable asymptotic expansion procedure [6], which makes homogenization of Maxwell's equations in a periodically composite under condition that a period tends to zero, is presented as purely mathematic one and does not discuss the problem of artificial magnetism from non–magnetic conductors. The author [7] has derived a productive transformed integral equation for the electric field in periodically microstructured composite, with inhomogeneous term being proportional to electric field averaged over unit cell of the microstructure and integrating over unit cell in the integral term. This equation was solved numerically to get the spatially dispersive effective dielectric permittivity tensor and to consider, in particular, effective magnetic permeability via the spatial dispersion of dielectric permittivity according to [8]. In [9], a semi–intuitive approach is constructed to solve analytically the transformed integral equation [7], with obtaining some generalization of classical Lorentz–Lorenz formula for local electric field and similar formula for local magnetic field that gave possibility to obtain a corresponding generalization of the Clausius–Mossotti formulas for the classical "local" effective permittivity and permeability.

So far the approaches were discussed to homogenizing the Maxwell's equations in a periodically composites, with averaging over crystal cell. The aim of this paper is to show the systematic and clear way for effective magnetism with diamagnetic property definition in framework of electromagnetic wave multiple scattering theory by spatially disordered composites consisted of non–magnetic particles, each of which is characterized by given dielectric permittivity and conductivity. The wave multiple scattering theory [10, 11] starts with considering the wave scattering by a single particle that can be described in terms of particle tensor electric field scattering operator [12]. The principal point for our consideration is that this scattering operator is restored from Mie solution [13] for electromagnetic wave scattering field in all points of spherical particle outside, including near zone, in part of electric dipole and magnetic dipole scattering, that is with accounting the spherical harmonics of unit angular momentum. As this takes place, the contribution of electric dipole scattering into electric field scattering operator in momentum space representation is appeared to be not dependent on momentums whereas the contribution of magnetic dipole scattering is a bilinear function of scattering and incident momentums what is very suitable for effective magnetic permeability evaluation via effective dielectric permittivity tensor with quadratic spatial dispersion [8]. The effective dielectric permittivity tensor is evaluated in our formalism from generalized Lorentz-Lorenz formula, which is derived by homogenization of stochastic Maxwell's equations for electromagnetic field in random medium under consideration with using the technique of Dyson equation [10, 11] and averaging procedure over statistical ensemble of particles. Our observation the different contributions of a particle electric and magnetic dipole scattering into the transverse and longitudinal components of the effective dielectric permittivity is fundamental for appearance of an artificial effective diamagnetic properties in statistical ensemble of non–magnetic conducting particles. The authors [14] discuss similar phenomena in contribution of the electric–dipole and the magnetic–dipole transitions to the dielectric tensor in the framework of molecular light scattering.

In what follows we present the materials of our paper making accent on technique of generalized Lorentz–Lorenz formula related to statistical ensemble of non–magnetic conductive particles that can be especially useful at appearance a method [15] of artificial dielectric disordered material manufacturing with controlled parameters.

2 Homogenization of stochastic Maxwell's equations

We start with stochastic Maxwell's equations for monochromatic electromagnetic wave field

$$\mathrm{rot}\mathbf{E} = \mathbf{i}\,\frac{\omega}{\mathbf{c}}\,\mathbf{B}, \qquad \mathrm{rot}\mathbf{B} = -\mathbf{i}\,\frac{\omega}{\mathbf{c}}\,\hat{\varepsilon}\,\mathbf{E} \tag{1}$$

in homogeneous background (host) medium with frequency ω, constant dielectric permittivity ε_0 and unit magnetic permeability $\mu = 1$, where there are placed randomly particles with given dielectric permittivity ε_1, specific conductivity σ_1 and unit magnetic permeability. Symbol $\hat{\varepsilon}(\mathbf{r})$ denotes stochastic complex dielectric permittivity of the medium under study, being equal to complex dielectric permittivity $\hat{\varepsilon}_1 = \varepsilon_1 + i4\pi\sigma_1/\omega$ inside a single particle and ε_0 outside the particles. The problem of the random medium effective parameters is resolved by averaging the Eqs.(1) over particle spatial distribution statistical ensemble, with the averaging denoted as $\langle \dots \rangle$. In particular, an effective dielectric permittivity of the medium ε_{eff} is obtained according to [10, 11, 16, 17] via a "decoupling"

$$\langle \hat{\varepsilon}(\mathbf{r})\mathbf{E}_\alpha(\mathbf{r})\rangle = \int d\mathbf{r}'\, \varepsilon^{\mathbf{eff}}_{\alpha\beta}(\mathbf{r},\mathbf{r}')\ \langle \mathbf{E}_\beta(\mathbf{r}')\rangle \tag{2}$$

the averaged product $\langle \hat{\varepsilon} E_\alpha \rangle$ of the random medium complex dielectric permittivity and the random electric field vector $E_\alpha(\mathbf{r})$ with components $\alpha = 1, 2, 3$. As one can see, effective dielectric per-

mittivity of the random medium is a tensor operator, with tensor indices being denoted by Greek subscripts and implied agreement about summing over repeated subscripts. The decoupling (2) is realized with the aid of the Dyson equation [10, 11], which is obtained via ensemble averaging the integral equation for stochastic electric field and written in a symbolic operator form as

$$\langle E \rangle = E^{(0)} + G^{(0)} M \langle E \rangle \tag{3}$$

In the right hand side of this equation $E^{(0)}_{\alpha}(\mathbf{r})$ denotes the incident electromagnetic wave electric field; the tensor Green function of electric field in the host medium is given by $G^{(0)}_{\alpha\beta}(\mathbf{r}) = (\delta_{\alpha\beta} + \bigtriangledown_{\alpha} \bigtriangledown_{\beta} / k_0^2)\ G_0(r)$, with $k_0 = \varepsilon_0^{1/2}\ \omega/c$ being the wave number in the host medium and $G_0(r) = \exp(ik_0 r)/(-4\pi r)$ a scalar Green function; $M_{\alpha\beta}(\mathbf{r}, \mathbf{r}')$ is the tensor mass operator. The effective dielectric permittivity and mass operator are connected between them by operator relation, $\varepsilon_{eff}/\varepsilon_0 = I$ - M/k_0^2, where I is the identical operator.

3 Lorentz–Lorenz formula

The tensor Green function $G^{(0)}$ of electric field in the host homogeneous medium is strongly singular in the origin point and decomposed [16, 18, 19] into delta Dirac function term $1/(3k_0^2)I$ and the principal part $\tilde{G}^{(0)}$. Substituting this singular tensor Green function into Dyson Eq.(3) leads to a transformed mass operator that is defined by $\tilde{M} = \left[I - \frac{1}{3k_0^2} M\right]^{-1} M$ and gives possibility to get for the effective dielectric permittivity an operator relation

$$(\varepsilon_{eff} + 2\varepsilon_0)^{-1} (\varepsilon_{eff} - \varepsilon_0) = -\frac{\tilde{M}}{3k_0^2} \equiv \frac{4\pi}{3} \nu_{eff} \tag{4}$$

which we call a generalized Lorentz–Lorenz formula. The transformed mass operator $\tilde{M}$ is evaluated by applying the Feynman diagrams technique [10, 11] or via equivalent method of asymptotic expansions [16, 17]. The mass operator asymptotic expansions are obtained from asymptotic expansions for ensemble averaged $\langle T \rangle$ electric field random scattering operator T of the medium and the equation $\langle T \rangle = \tilde{M} + \tilde{M}\tilde{G}^{(0)} \langle T \rangle$. According to definition [12], the scattering operator $T_{\alpha\beta}(\mathbf{r}, \mathbf{r}')$ satisfies the Lippmann–Schwinger type equation, $T = \tilde{V} + \tilde{V}\tilde{G^{(0)}}T$, where the medium transformed scattering potential $\tilde{V}$ is equal to sum of single particle transformed potentials $\tilde{V}_1(\mathbf{r})$ = -k_0^2 3 $[\hat{\varepsilon}_1(\mathbf{r}) - \varepsilon_{\mathbf{0}}]$ / $[\hat{\varepsilon}_1(\mathbf{r}) + \mathbf{2}\varepsilon_{\mathbf{0}}]$, provided that the particles are not overlapped.

4 Generalized and classical Lorentz–Lorenz formula

Making comparison between the obtained Lorentz–Lorenz formula (4) and the classical one [13] shows that a quantity ν_{eff} denoting the (4) right hand side has sense of the medium effective electric susceptibility per unit volume tensor operator. The ratio ν_{eff}/f_1, with f_1 being the particle number density, is an electric susceptibility per a scatterer. The left hand side of the generalized Lorentz–Lorenz formula is really looking like very familiar algebraic construction [13] and in the right hand side of this one stands the transformed mass operator, which includes all significant items influencing the dielectric and conducting properties of composites. Besides the frequency effects, i.e. accounting for intrinsic properties of constituency by their complex dielectric functions, the mass operator includes geometric effects, caused by resonant behavior of composite due to the shape and size of particles, as well as cluster effects because of correlations between particles, which can result

in significant modification of particle scattering properties. The obtained Lorentz–Lorenz formula includes such known cases as Maxwell–Garnett mixing rule with Clausius–Mossotti formula in the presence of multiple scattering on small correlated [18] and non–correlated [19] dielectric spheres. The case of non–correlated dielectric particles is described by transformed mass operator in the asymptotic form $\tilde{M} \approx \int d1 f_1 T_1$ where f_1 is related to a particle center $\mathbf{r_1}$ and T_1 is the single particle electric field scattering operator with transformed scattering potential $\tilde{V}_1(\mathbf{r} - \mathbf{r_1})$.

5 Effective magnetic permeability

If statistical ensemble of particles is homogeneous and isotropic in average, the operators ε_{eff} and $\tilde{M}$ are functions of spatial coordinates differences and can be expanded into Fourier integrals along spatial harmonics $\exp(i\mathbf{kr})$. Corresponding tensor Fourier transformations are defined by transversal t and longitudinal ℓ with respect to the wave vector $\mathbf{k}$ components, as $\varepsilon_{eff,\alpha\beta}(\mathbf{k}) = (\delta_{\alpha\beta} - \hat{k}_\alpha \hat{k}_\beta)\ \varepsilon^t_{eff}(k) + \hat{k}_\alpha \hat{k}_\beta\ \varepsilon^\ell_{eff}(k)$, with $\hat{k}$ being the unit vector along $\mathbf{k}$. In terms of these components the Lorentz–Lorenz formula (4) reads

$$\frac{\varepsilon^{t,\ell}_{eff}(k) - \varepsilon_0}{\varepsilon^{t,\ell}_{eff}(k) + 2\varepsilon_0} = -\frac{\tilde{M}^{t,\ell}(k)}{3k_0^2} \tag{5}$$

Actually, one does see in the left hand side of this formula the transversal and longitudinal effective dielectric permittivities [8, 14] for a monochromatic plane wave.

The spatial transversal and longitudinal Fourier components of the transformed mass operator in the right hand side of Eq.(5) take in the case of non–correlated (independent) particles the form $\tilde{M}^{t,\ell}(k) = f_1\ T^{t,\ell}(\mathbf{k}, \mathbf{k})$. Note, a quantity $T_{\alpha\beta}(\mathbf{k}, \mathbf{k}')$ denotes the electric field tensor scattering operator of a single particle in spatial Fourier transform (momentum) representation with arbitrary wave vectors $\mathbf{k}$ and $\mathbf{k}'$. After having been restricted on wave vector spherical surface $\mathbf{k} = \mathbf{k}' = k_0$, the double transversal part of this tensor with respect to directions of both scattering and incident wave vectors gives the tensor scattering amplitude in far wave zone of the particle [12]. Nevertheless, we have met the tensor scattering operator $T_{\alpha\beta}(\mathbf{k}, \mathbf{k})$ for forward scattering direction, when the both wave vectors are identical and not equal to the wave number in the host medium with respect to their absolute magnitudes. We made supposition that this value of the tensor scattering operator is defined by its transversal and longitudinal components $T^{t,\ell}(\mathbf{k}, \mathbf{k})$ that is correct, for example, in the case of a spherical particle. Following [8] we denote

$$1 - \frac{1}{\mu_{eff}} = \frac{\omega^2}{c^2}\,\frac{\varepsilon^t_{eff}\,(k) - \varepsilon^\ell_{eff}\,(k)}{k^2} = \frac{\left[\tilde{M}^t\,(k) - \tilde{M}^\ell\,(k)\right]/k^2}{\left[1 + \tilde{M}^t\,(k)\,/3k_0^2\right]\ \left[1 + \tilde{M}^\ell\,(k)\,/3k_0^2\right]} \tag{6}$$

setting next $4\pi\mathbf{I}(\mathbf{k}) = (1 - 1/\mu_{eff})\langle\mathbf{B}(\mathbf{k})\rangle$ and rewriting the ensemble averaged second Maxwell's Eq.(1) identically as

$$i\,\mathbf{k} \times (\langle\mathbf{B}(\mathbf{k})\rangle - \mathbf{4\pi I}(\mathbf{k})) = -\frac{\mathbf{i}\omega}{\mathbf{c}}\varepsilon^\ell_{\mathbf{eff}}(\mathbf{k})\,\langle\mathbf{E}(\mathbf{k})\rangle \tag{7}$$

Eq.(6) defines in the limit $k \to 0$ an effective magnetic permeability μ_{eff}, with $\mathbf{I}(\mathbf{k})$ being a vector of effective medium magnetization. In result, Eq.(7) takes a form of the macroscopic Maxwell's equation with magnetic flux vector [20], given by $\langle\mathbf{H}(\mathbf{k})\rangle = \langle\mathbf{B}(\mathbf{k})\rangle$ - $4\pi\mathbf{I}(\mathbf{k})$ and dielectric displacement current defined by longitudinal component of effective dielectric permittivity.

6 Electric dipole and magnetic dipole scattering

Let us evaluate the effective magnetic permeability defined by (6) in the case of independent spherical particles. Instead to find a solution to the Lippmann–Schwinger equation we will construct here the single particle scattering operator T_1 in approximation of electric dipole and magnetic dipole scattering. The incident electromagnetic wave induces into the particle the electric dipole and magnetic dipole moments $\mathbf{p} = \varepsilon_0\eta\mathbf{E_0}$ and $\mathbf{m} = \chi\mathbf{H_0}$ with dielectric and magnetic susceptibilities η and χ, respectively. The Hertz's vector of electric dipole and magnetic dipole scattering $\Pi_\alpha^{(el)}(\mathbf{r})$ and $\Pi_\alpha^{(mag)}(\mathbf{r})$ is given according to [21] by $\Pi_\alpha^{(el)}(\mathbf{r})$ = - $(4\pi/\varepsilon_0)p_\alpha G_0(r)$ and $\Pi_\alpha^{(mag)}(\mathbf{r})$ = - $(4\pi/ik_0\varepsilon_0^{1/2})\mathrm{e}_{\alpha\beta\gamma}m_\beta\nabla_\gamma G_0(r)$, respectively, where $\mathrm{e}_{\alpha\beta\gamma}$ is absolute anti-symmetric unit tensor. Bearing in mind the rule to evaluate the electric wave field via the Hertz' vector and also via the scattering operator, $E = G^{(0)}T_1E^{(0)}$, one can get the following expressions for scattering operators of electric dipole and magnetic dipole scattering, respectively, in the form

$$T_{\alpha\beta}^{(el)}(\mathbf{r},\mathbf{r}') = -\,\mathbf{4\pi k_0^2}\,\eta\,\delta(\mathbf{r})\delta(\mathbf{r}')\delta_{\alpha\beta},$$
$$T_{\alpha\beta}^{(mag)}(\mathbf{r},\mathbf{r}') = -\,\mathbf{4\pi}\chi\,\mathrm{e}_{\alpha\xi\eta}\,\mathrm{e}_{\beta\xi\gamma}\,\nabla_\eta\nabla_\gamma'\delta(\mathbf{r})\delta(\mathbf{r}'). \tag{8}$$

The evident expressions of spherical particle electric and magnetic susceptibilities η and χ are written out by comparison with Mie solution [13] for electromagnetic wave scattering in all points of particle outside and have in Hulst [22] partial scattering amplitudes the form $\eta = (3i/2k_0^3)a_1$ and $\chi = (3i/2k_0^3)b_1$. The transversal and longitudinal components of the obtained scattering operators in momentum representation for forward scattering direction are given by

$$T^{(el)t}(\mathbf{k},\mathbf{k}) = \mathbf{T^{(el)\ell}}(\mathbf{k},\mathbf{k}) = -\,\mathbf{4\pi}\,\eta\,\mathbf{k_0^2};$$
$$T^{(mag)t}(\mathbf{k},\mathbf{k}) = -\,\mathbf{4\pi}\chi\,\mathbf{k^2},\ \mathbf{T^{(mag)\ell}}(\mathbf{k},\mathbf{k}) = \mathbf{0}. \tag{9}$$

As one see, the electric dipole gives equal contributions into transversal and longitudinal components of the scattering operator in momentum representation for forward scattering direction but the magnetic dipole contributes into the transversal component only. As consequence the difference, $\tilde{M}^t(k)$ - $\tilde{M}^\ell(k)$ = - $4\pi f_1\chi k^2$, includes contribution of magnetic dipole scattering only. As result the Eq.(6) for effective magnetic permeability takes a form

$$1 - \frac{1}{\mu_{eff}} = \frac{4\pi f_1\chi}{\left[1 - (4\pi/3)f_1\eta\right]^2} \tag{10}$$

7 Effective diamagnetism

The electric and magnetic susceptibilities of spherical particle with radius r_0 small compared to the wavelength in the host medium are given according to [13, 22] by $\eta = r_0^3$ and χ = - $(1/2)r_0^3$, respectively, in the limit of perfectly reflection because of high dielectric permittivity or conductivity of the particle. These electric and magnetic susceptibilities of a spherical particle lead to effective diamagnetism of random medium consisting of such particles due to the Eq.(10). In the limit of small filling fraction, $f_1 r_0^3 << 1$, these equation gives formula $\mu_{eff} \approx 1 + 4\pi f_1\chi$, obtained in [3] yet. The Eq.(10), with ignoring contribution of electric susceptibility in the right hand side denominator, coincides in the form with a formula [23] for electron diamagnetism effect. The denominator in the right hand side of the Eq.(10) leads to the diamagnetism enhancement because existence of effective dielectric permittivity given according to Eq.(5) by $(\varepsilon_{eff}^\ell - \varepsilon_0)$ / $(\varepsilon_{eff}^\ell + 2\varepsilon_0) = (4\pi)/3)$ $f_1\ \eta$. One can say that diamagnetism is enhanced by appearance of additional effective dielectric displacement current in the medium.

8 Conclusion

In this paper the physical nature of diamagnetic property in the effective magnetic permeability at coherent electromagnetic wave multiple scattering by statistical ensemble of independent perfectly reflected non–magnetic small spherical particles has been revealed. The diamagnetic physical nature consists in that the electric dipole scattering by a particle gives equal contributions into transversal and longitudinal components of the effective permittivity whereas the magnetic dipole scattering contributes into the transversal component only. This observation is made with the aid of generalized Lerentz–Lorenz formula technique for effective dielectric permittivity with spatial dispersion.

Acknowledgments

This work was supported in part by Russian Foundation for Basic Research, Grant 09-02-00920-a and 09-02-12433-OFIM, by the Russian Academy of Sciences projects "Passive multichannel human radio- and acousto-thermotomography in near zone" and "Investigations of new types of photonic crystals for the development of optoelectronic elements of infocommunicationic nets".

References

[1] R. A. Shelby, D. R. Smith, S. Schultz, Science, **77**, 292 (2001)

[2] D. R. Smith, W. J. Padilla, D. C. Vier, S. C. Nemat-Nasser, S. Schultz, Phys. Rev. Lett., **84**, 4184 (2000)

[3] S. A. Schelkunoff, H. T. Friis, *Antennas: theory and practice*, John Wiley, New York (1952)

[4] M. V. Kostin, V. V. Shevchenko, *Proc. Bianisotropics'94*, Perigueux, France, 2075 (1999)

[5] J. B. Pendry, A.J. Holden, D.J. Robbins, W. J. Stewart, IEEE Trans. Microwave Theory Tech., **47**, 2075 (1999)

[6] A. Bensoussan, J. L. Lions, G. Papanicolaou, *Asymptotic Analyssis for Periodic Structures (Studies in mathematics and its applications)*, **5**, North-Holland (1978)

[7] M. G. Silveirinha, Phys. Rev. B, **75**, 115104 (2007)

[8] L. D. Landau and E. M. Lifshitz, *Electrodynamics of Continuous Media, Course of Theoretic Physics*, **8**, Elsevier, Oxford/ Butterworth-Heinemann (2004)

[9] M. G. Silveirinha, Phys. Rev. B, **76**, 245117 (2007)

[10] U. Frish, Ann. d'Astrophys., **29**, 645 (1966)

[11] U. Frish, Ann. d'Astrophys., **30**, 565 (1967)

[12] R. G. Newton, *Scattering Theory of Waves and Particles*, McGraw–Hill, New York (1966)

[13] M. Born, E. Wolf *Principles of Optics*, Pergamon Press, New York (1964)

[14] V. M. Agranovich, Yu. N. Garstein, Sov. Phys.–Usp., **49**, 10 (2006)

[15] S. Matitsine, *An artificial dielectric material and a method of manufacturing the same*, U.S. Patent No. WO/2009/078807 A1 (2009)

[16] V. M. Finkelberg, JETP, **26**, 268 (1968)

[17] Yu.N. Barabanenkov, Sov. Phys.–Usp., **118**, 673 (1976)

[18] V. M. Finkelberg, Journal of Technical Physics, **34**, 509 (1964)

[19] P. Mallet, C. A. Guerin, A. Sentenac, Phys. Rev. B, **72**, 014205 (2005)

[20] J. D. Jackson, *Classical Electrodynamics*, Wiley, New York (1998)

[21] J.A. Stratton, *Electromagnetic Theory*, McGraw–Hill, New York (1941)

[22] H.C. van de Hulst, *Light Scattering by Small Particles*, John Wiley, New York (1957)

[23] I. E. Tamm, *Foundations of the Theory of Electricity*, Gostekhizdat, Moscow-Leningrad (1946)